

Acuity 85 (oprifocon A)

Indications	Characteristics		Lens Parameters	
<ul style="list-style-type: none"> • Myopia • Hyperopia • Astigmatism • Presbyopia • Keratoconus • Pellucid Marginal Degeneration • Post Penetrating Keratoplasty • Post RK • Post Lasik 	Oxygen Permeability (Dk*)	115	Chord Diameter Range	7.0 to 21.0mm
	Refractive Index	1.422	Center Thickness Range	0.07 to 0.65mm
	Hardness (Shore D)	81	Base Curve Range	4.00 to 11.50mm
	Specific Gravity	1.23	Power Range	-20.00 to +20.00D
	Wetting Angle**	103/35	Add Powers	+1.00 to +4.00D
	Light Transmittance*** [Average %T (380-780nm)]	81	Water Content	< 1%
	<small>*ISO/Fatt Method: $DK_{Units} = \times 10^{-8} \frac{(cm^3 O_2)(cm)}{(sec)(cm^2)(mmHg)}$ @ 35°C; **Sessile Drop per ANSI Z80.20, 8.11; ***ISO8599: 1994</small>			

Available Tints	Standard Diameter	
	Blue	Green
ACUITY 85 (oprifocon A)	✓	✓

Acuity
Polymers

1-888-POLYMER • www.acuitypolymers.com

Acuity Polymers, Inc. | 1667 Lake Avenue, Building 59, Suite 303 | Rochester, NY 14615, USA